

Technical Data Sheet

KEMOPOL PREMIUM PROTECT

High-quality washable paint for interior walls with protection against the development of fungi and mold



product description:	High-quality dispersive paint for interior walls with effective additional protection against the development of mold on the surface of the coating, very high coverage. It creates a firm, durable and elastic film that is washable, i.e. resistant to wet rubbing, so that it is possible to wipe not overly accepted soiling with a cloth soaked in a solution of universal cleaning agents.									
area of application:	It is intended for the protection and decoration of all types of interior wall surfaces, and is especially recommended for areas where there is an increase in air humidity and water vapor condensation. Thanks to its resistance to washing, it is particularly suitable for areas exposed to heavy loads (corridors, staircases, hospitals, canteens, restaurant kitchens, saunas, walls around indoor pools, etc.). Kemopol Premium Protect is used only to prevent the formation of mold. If it is necessary to treat an already infected wall, it is necessary to apply <i>Algenon</i> or <i>Algenon plus</i> an agent for the rehabilitation of walls from fouling.									
product range:	It is produced in white colour and by using tinting system <i>Top Mix</i> , it is possible to achieve wide range of shades from the Chromos-Svjetlost colour chart and many other on the market. Tinting is possible with the use of pigment preparations <i>Kemoton Strong</i> and <i>Kemoton Plus</i> .									
dilution:	Pure water, max. 5 %.									
spreading rate:	5–6 m ² /l in two layers, depending on the absorbency and roughness of the substrate.									
non-volatile-matter content:	68 ± 2 % (EN ISO 3251)									
density:	1.55–1.6 kg/l (EN ISO 2811-1)									
volatile organic compounds content (VOC):	A(a) 30 g/l; max. 1 g/l (EN ISO 11890-1)									
technical data according to EN 13300:	<table border="1"> <tr> <td>Max. grain size (granularity) (EN ISO 1524)</td> <td>Fine < 100 µm</td> </tr> <tr> <td>Wet scrub resistance (EN ISO 11998)</td> <td>Class 2</td> </tr> <tr> <td>Opacity (EN ISO 6504-3)</td> <td>Class 3 with declared spreading rate</td> </tr> <tr> <td>Gloss (EN ISO 2813)</td> <td>Matt</td> </tr> </table>		Max. grain size (granularity) (EN ISO 1524)	Fine < 100 µm	Wet scrub resistance (EN ISO 11998)	Class 2	Opacity (EN ISO 6504-3)	Class 3 with declared spreading rate	Gloss (EN ISO 2813)	Matt
Max. grain size (granularity) (EN ISO 1524)	Fine < 100 µm									
Wet scrub resistance (EN ISO 11998)	Class 2									
Opacity (EN ISO 6504-3)	Class 3 with declared spreading rate									
Gloss (EN ISO 2813)	Matt									
working conditions:	The temperature of the air, material and surface during processing must be higher than +5 °C and lower than +30 °C, and the relative humidity lower than 80 %. Low temperatures as well as high air humidity prolong the drying time and can change the shade unevenly. High temperature in summer shorten the open working time of the material.									
substrate preparation:	The substrate must be completely dry, smooth, clean, free of loose parts, dust, grease stains, mold and other foreign bodies. Before each painting, the substrate must be inspected and its condition determined. All loose parts of the substrate and old coatings should be removed. The resulting unevenness, depending on their depth, fill with suitable plasters or leveling compounds. New substrates made of lime-cement mortars must be dried for a minimum of 14 days, levelling compounds for a minimum of one day per millimetre of thickness, and new concrete substrates for a minimum of one month. Treat mould infected substrates with biocide solution <i>Algenon</i> or <i>Algenon Plus</i> , then clean with a cloth or a brush using solution of universal cleaners. The most effective									

Technical Data Sheet

KEMOPOL PREMIUM PROTECT

High-quality washable paint for interior walls with protection against the development of fungi and mold



solution against the formation of mold is to eliminate the cause of their formation (regular ventilation, insulation of cold bridges, removal of moisture sources, waterproofing). Wash greasy and heavily soiled parts with solution of *Kaljev sapun*. Glossy and water-repellent coatings should be pre-roughened with sandpaper. New substrates should be impregnated with *Simpra universal primer* (ratio 1:3) and when painting inhomogeneous substrates with intensive shades of lower coverage (yellow, orange, red...), *Simpra grundmix primer* should be pre-applied in a shade approximately to the shade of Kemopol Premium Protect finish. Apply Kemopol Premium Protect on a completely dry surface at least 6 hours after applying the impregnation, depending on the weather conditions.

material preparation and application: Before use, mix the material in the original packaging with a slow rotating mixer. If necessary, dilute with water to the desired consistency for application, maximum 10%. The product is usable even at higher dilutions, but certain material properties can no longer be achieved (degree of gloss, opacity, degree of whiteness, abrasion resistance, etc.). The substrate must be firm, dry, smooth and clean. Kemopol Premium Protect is applied with paint brush, paint roller (fibre length between 18-20 mm) or airless spray in two layers. When using a roller use a suitable paint roller net.

The second layer is applied only when the previous one is completely dry (approx. 4-6 h). On one surface apply products from the same production batch. **Different production batches, as well as products tinted in the Top Mix system, must be cross mixed before use.**

For use, prepare a quantity of the product that is sufficient to process one surface, store the rest in a well-sealed original packaging. Never store already diluted product! When applying the material by spraying, it is necessary to use protective equipment (goggles, respiratory protection, protective mask). To avoid visible joints and traces of a roller or brush, we recommend applying wet on wet, without interruption from one edge of the surface to the other. Subsequent repairs are not allowed. We recommend first applying the paint along the edges of the walls with a brush, then applying the paint with a roller while leveling the joint. Additional paint correction during the application is not allowed (dilution, addition of colorants, etc.).

Wash the tool immediately after working.

Adhere to the applicable construction standards when applying the products.

For any additional info, please contact a Chromos-Svjetlost technical advisor.

coatings drying: Intercoating interval 4-6 h (20 °C and relative humidity 65 %). Complete drying of coatings in 6-12 h (20°C and relative humidity 65%). The specified period may be extended depending on the weather conditions.

surfaces maintenance: Maintain surfaces by dusting and cleaning. On surfaces from which dirt or stains cannot be removed, it is necessary to perform restorative painting (new two-layer application of paint, see the substrate preparation).

safety measures: It is necessary to follow the general rules for construction works. Keep out of reach of children. Wear protective equipment. Read the product safety data sheet before use.

transport and storage: Store in a dry and well-ventilated place out of direct sunlight at a temperature of +5 to +25 ° C. Protect it from freezing.

shelf life: In unopened packaging 18 months.

product/packaging disposal: Empty the packaging completely and hand over to the recycling yard. Dispose of in accordance with valid regulations to an authorized waste collector.

quality control: Product quality characteristics are determined by internal production specifications, as

Technical Data Sheet

KEMOPOL PREMIUM PROTECT

High-quality washable paint for interior walls with protection against the development of fungi and mold



	well as European and Croatian standards. The product is under the constant supervision of factory quality control Chromos-Svjetlost d.o.o.
other information:	Mechanical damage to dark shades causes the appearance of light streaks. The described phenomenon is specific to dark shades and does not affect the quality of the coating.
disclaimers:	<p>Technical values refer to basic products. Tinting the product may cause minor deviations in certain technical characteristics. Depending on the properties of the substrate and the method of application of the product, minor deviations in shade in relation to the tone chart are possible. The product shade should be checked on a small test surface before use, as we will not be able to accept any subsequent complaints.</p> <p>Before using the product, please check its quality. In case of any major deviations from the declared properties of the product, stop the use and contact the manufacturer; otherwise any subsequent complaints will not be accepted.</p> <p>Technical data are the result of our technical and experimental knowledge, and are provided with the intention of achieving optimal results in working with CHROMOS-SVJETLOST products. The data does not contain a legal or secondary obligation of the manufacturer nor does it release the user from the obligation to check the suitability of the product for particular purpose. Due to the use of natural raw materials in our products, minor deviations from certain values are possible for individual deliveries. Contact our Technical service before use on substrates not listed in the accompanying documentation. The manufacturer reserves the right to make any subsequent changes to the Technical Data Sheet. Only the latest edition is valid. Updated Technical Data Sheets can be found on the website www.chromos-svjetlost.hr or can be requested from the manufacturer via the contact e-mail address below. Contact our Technical service for more detailed information. Be sure to read the safety labels on the product packaging before use. Safety Data Sheet is available on request.</p>

October, 2021.

Quality and Environmental management systems certified in accordance with TÜV NORD Croatia;
Certificate No: 44 100 134668 / 44 104 134668

